

The world leading supplier of tungsten products

## Products Introduction

### Ammonium Paratungstate - APT

Physical properties

1、APT-A type Apparent density: 1.6-2.4g/cm<sup>3</sup> The range may be the customer  
FSSS:30-50um

We can meet other requirements of the customers regarding sieve analysis etc.

2、APT-B type Apparent density: 1.9-2.5g/cm<sup>3</sup> The range may be the customer  
FSSS:40-50um

Hall flowability: 30-40s/50g

We can meet other requirements of the customers regarding sieve

#### Chemical composition:

Elements	Content max (%)
Al	0.0005
As	0.0007
Bi	0.0001
Ca	0.0007
Cd	0.0001
Cr	0.0005
Co	0.0005
Cu	0.0001
Fe	0.001
Mg	0.0005
Mn	0.0005
Mo	0.002
Na	0.0007
Ni	0.0005
K	0.001
P	0.0007
Pb	0.0001
S	0.0007
Sb	0.0002
Si	0.001
Sn	0.0001
Ti	0.0005
V	0.0005

Packing in iron drums with inner cloth bags or plastic bags of 50kgs, 100kgs or 200kgs net each.