

---

The world leading supplier of tungsten products

## Products Introduction

### RTP composition and properties :

Grade	ISO grade	WC%	CO%	Tic%	Tac%	Others	Scott Density	Flow rate sec/50g	Harsness HRA ±0.5	Density g/c m3 ± 0.1	TRS Mpa Min
XLU15UF		90.5	8.0			1.5	3.00	24-30	93.2	14.60	35000
XLU25UF		86.0	12.0		12.0	0.8	2.70	25-32	93.0	14.10	4000
XLU10	K01	94.0	6.0				3.20	24-30	93.0	14.85	2700
XLU20	K20	90.0	10.0				3.10	24-30	92.0	14.45	3400
XLU30	K20	86.5	13.5				3.00	25-30	90.5	14.00	3500
XLK02	K02	96.0	4.0				3.40	21-25	92.5	15.15	2300
XLK05	K10	94.0	6.0				3.30	21-26	92.0	14.95	2450
XLK10	K10	94.0	6.0				3.40	21-25	91.5	14.95	2500
XLK20	K20	94.0	6.0				3.40	21-26	91.0	14.95	2600
XLK30	K30	92.0	8.0				3.40	21-26	90.0	14.70	2700
XLK40	K40	91.0	9.0				3.30	21-26	89.0	14.60	2800
XLF20		94.0	6.0				3.30	21-26	90.0	14.95	2600
XLF25		92.0	8.0				3.40	21-26	89.5	14.70	2150
XLF25D		92.0	8.0				3.30	21-28	89.0	14.70	2800
XLF35	K40	89.0	11.0				3.30	21-27	88.5	14.45	2900
XLF40	K40	88.0	12.0				3.30	21-28	89.0	14.40	3000
XLF70A		75.5	25.0				3.50	21-26	81.5	13.15	2400
XLD10		94.0	6.0				3.40	21-25	89.0	14.95	2500
XLD20		92.0	8.0				3.40	21-26	88.52	14.70	200
XLD25		90.0	10.0				3.50	22-28	87.5	14.50	2850
XLD40		87.0	13.0				3.40	24-30	86.5	14.20	3200
XLD50		85.0	15.0				3.20	24-30	86.0	14.00	3100
XLT20	P20	72.0	8.0	8.0	12.0				92.2	12.55	1900
XLT30	P30	75.8	8.0	6.2	10.0				91.5	12.90	2100
XLT40	P40	80.0	10.0	5.0	5.0				90.5	13.10	2200