


The world leading supplier of tungsten products

Products Introduction

Tungsten Metal Powder

Various grades of W powder from 0.2 μ to 60 μ .

Physical properties



The world leading supplier of tungsten products**1 μ - 9 μ tungsten powder :**

Grade	F.s.s.s	Oxygen% max
XLW10	0.9-1.1	0.20
XLW13	1.2-1.4	0.15
XLW15	1.4-1.7	0.12
XLW20	1.8-2.2	0.08
XLW25	2.3-2.7	0.08
XLW30	2.8-3.2	0.06
XLW35	3.3-3.7	0.06
XLW40	3.8-4.5	0.04
XLW50	4.6-5.4	0.04
XLW55	5.0-6.0	0.04
XLW60	5.5-6.5	0.04
XLW65	6.0-7.0	0.04
XLW70	6.5-7.5	0.04
XLW80	7.5-8.5	0.04
XLW90	8.5-9.5	0.04

Coarse tungsten powder :

Grade	F.s.s.s	Oxygen% max
XLW100	9-11	0.04
XLW120	11-13	0.10
XLW150	13-19	0.10
XLW200	16-24	0.10
XLW300	25-35	0.12
XLW500	40-60	0.15

Ultra-fine and micron tungsten powder:

Grade	BET or F.s.s.s	Oxygen% max
XLW02	>5.0 m ² /g	0.80
XLW04	4.0-5.0 m ² /g	0.60
XLW05	0.5-0.6 μ m	0.55
XLW06	0.6-0.7 μ m	0.40
XLW07	0.7-0.8 μ m	0.35
XLW08	0.8-0.9 μ m	0.25

Packing in iron drums with inner plastic bags of 50kgs, 100kgs or 200kgs net each.