


The world leading supplier of tungsten products

Products Introduction

Tungsten Metal Powder

Various grades of W powder from 0.2 μ to 60 μ .

Physical properties



The world leading supplier of tungsten products**1 μ - 9 μ tungsten powder :**

| Grade | F.s.s.s | Oxygen% max |
|-------|---------|----------------|
| XLW10 | 0.9-1.1 | 0.20 |
| XLW13 | 1.2-1.4 | 0.15 |
| XLW15 | 1.4-1.7 | 0.12 |
| XLW20 | 1.8-2.2 | 0.08 |
| XLW25 | 2.3-2.7 | 0.08 |
| XLW30 | 2.8-3.2 | 0.06 |
| XLW35 | 3.3-3.7 | 0.06 |
| XLW40 | 3.8-4.5 | 0.04 |
| XLW50 | 4.6-5.4 | 0.04 |
| XLW55 | 5.0-6.0 | 0.04 |
| XLW60 | 5.5-6.5 | 0.04 |
| XLW65 | 6.0-7.0 | 0.04 |
| XLW70 | 6.5-7.5 | 0.04 |
| XLW80 | 7.5-8.5 | 0.04 |
| XLW90 | 8.5-9.5 | 0.04 |

Coarse tungsten powder :

| Grade | F.s.s.s | Oxygen% max |
|--------|---------|----------------|
| XLW100 | 9-11 | 0.04 |
| XLW120 | 11-13 | 0.10 |
| XLW150 | 13-19 | 0.10 |
| XLW200 | 16-24 | 0.10 |
| XLW300 | 25-35 | 0.12 |
| XLW500 | 40-60 | 0.15 |

Ultra-fine and micron tungsten powder:

| Grade | BET or F.s.s.s | Oxygen% max |
|-------|---------------------------|----------------|
| XLW02 | >5.0 m ² /g | 0.80 |
| XLW04 | 4.0-5.0 m ² /g | 0.60 |
| XLW05 | 0.5-0.6 μ m | 0.55 |
| XLW06 | 0.6-0.7 μ m | 0.40 |
| XLW07 | 0.7-0.8 μ m | 0.35 |
| XLW08 | 0.8-0.9 μ m | 0.25 |

Packing in iron drums with inner plastic bags of 50kgs, 100kgs or 200kgs net each.